


ENG
Arabic

DESCRIPTION

PORCELAINFIX is a high-performance, flexible, polymer-modified, cement-based adhesive for all tile types. Characterized by extended open time, no vertical slip for ceramic tiles.

FIELDS OF APPLICATION

PORCELAINFIX is suitable for fixing all types of ceramic tiles, natural stone, marble, granite and porcelain on cementitious renders, cementitious screeds and concrete.
Suitable for porcelain & ceramic tiles with size (10x10cm - 20x20cm - 30x30cm - 30x60cm - 30x90cm - 30x120cm - 40x40cm - 50x50cm - 60x60cm - 80x80cm - 60x120cm)
Suitable for walls and floors.
Suitable for indoor and outdoor applications.

DIRECTIONS FOR USE

-**Substrate** the surface to be overlaid must be clean, free of dust, grease, paint, loose material, etc. Dampening of the substrate before application is recommended.

- **PORCELAINFIX** is gradually added into water under continuous stirring for 3-5 min until a uniform paste is formed (Creamy thixotropic mortar). A low speed mixer is recommended for mixing. The mixture should be left at least for about 5 minutes to settle and slightly stirred again for 1 min, the paste is ready for application.

-**Application** To obtain a good adhesion first apply a thin coat of paste with the flat side of trowel create a layer approximately 1 mm thick, then notch with the toothed side of trowel. The tiles should be fixed by pressing to the desired position. In any case, consider that 75-80% of the reverse side of tiles needs to be covered for interior installations, and 100% for exterior installations or floors subject to heavy traffic.

-**Fix** the tile with a firm pressure. Open time is 5 - 20 minutes, climatic conditions can reduce or extend this time, If this period is exceeded get rid of the mortar, because it's no longer suitable to use.

-**Applied** mixture must be covered within 30 minutes in order to avoid "skin" formation.

-**Back-buttering** - For exterior installations, large-size tiles (greater than 30x30cm), floors with intense or heavy traffic, vibrating supports and situations exposed to high temperature fluctuations, the adhesive mortar must be applied to both the substrate and the back of the tiles so as to obtain a full layer of adhesive without any air pockets.

WARNINGS

Protective equipment

-Safety equipment must be used by the applicant during the application which includes respirator mask, safety glasses and gloves during application and any other safety tools if required.

-Do not add lime, cement or other foreign materials to the product.
-Do not use the product to create layers more than 6 mm thick.
-Do not use the product for applications not stated in this technical data sheet.
-If in doubt, contact the help service. Numbers are available below.
-Very porous surfaces, such as aerated concrete, gypsum boards, chipboards, etc., must be primed first with PRIMER.

The technical information and instructions supplied here and the datasheet are based on the knowledge and experience of the Research and Development Department of our factory. Due to wide variety of individual application conditions, the recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our factory. The user alone is responsible for any consequences deriving from the use of the product.

بورسلين فكس ملطف اسمنتى الأساس ذو الأداء العالى، ومرنة، مدمعة بمادة البوليمير للصلق معظم أنواع البلاط. و بميزة (بدون انزلاق عمودي) للسيراميك و قابل التطبيق لمدة طويلة.

مجالات الاستخدام

بورسلين فكس مناسب لتشييد معظم أنواع وأحجام السيراميك والجرانيت والبلاط والبورسلين على الطلاءات الإسمنتية والألواح الأرضانية والخرسانية.
مناسب لبلاط البورسلين والسيراميك بالحجم 10x10 سم - 20x20 سم - 30x30 سم - 90x30 سم - 120x30 سم - 50x50 سم - 60x60 سم - 80x80 سم
مناسبة للجدران أو الأرضيات
مناسبة للستخدام الداخلي والخارجي.

تعليمات الإستخدام

المادة المتفاعلة: يجب أن يكون السطح نظيفاً و خالي من الغبار والشحوم والطلاء و الماء السائبة. يوصى بلطف الطبيقة قبل التطبيق.

- **يضاف منتج بورسلين فكس** تدريجياً إلى الماء تحت التحريك المستمر 5-3 دقيقة حتى يتم تشكيل عجينة موحدة. يوصى باستخدام خلاط منخفض السرعة للخلاط. يجب ترك الخليط لمدة 5 دقائق أو أكثر حتى يستفحل جيداً ويخلط مرة أخرى لمدة 1 دقيقة و يكون المعجون جاهز للتطبيق.

التطبيق: للحصول على التصاق جيد، يجب أولاً وضع طبقة رقيقة من المعجون مع الجانب المسطح من المجرفة (المالج)، قم بإنشاء طبقة بسمك حوالي 1 مم، ثم الشق مع جانب الخشن من المجرفة (المالج)، يجب تثبيت السيراميك بضغطه عليه في المكان المطلوب. يجب أن تكون في اعتبار أن 75-80٪ من الجانب العكسي (الخلفي) للبلاط يحتاج إلى تغطية بالمعجون للتراكيب الداخلية، و 100٪ من التراكيب الخارجية أو الأرضيات التي تخضع لحركة المرور الكثيفة.

- **يجب ثبات البلاط** بضغط ثابت. تعدد فترة الرغبة من 5 إلى 20 دقيقة، يمكن للظروف المناخية أن تقلل أو تمتد هذه الفترة، إذا تمتجاوز هذه الفترة تخلص من الملطف، لأنه لم يعد مناسباً للستخدام.

- **يجب أن يغطي الخليط المطبق** بالبلاط في غضون 30 دقيقة لتجنب تشكيل "الجلد".

تطبيق المعجون على الجهة الخلفي من البلاط: للتركيبات الخارجية، البلاط كبير الحجم (أكبر من 30 × 30 سم)، والأرضيات المماكن المزدحمة بالمرور، والماكين معرضة لنقبات درجات الحرارة العالية، يجب تطبيق المعجون على جزء الخلفي من البلاط وذلك للحصول على كامل طبقة لاصقة قوية دون أي فراغات الهواء.

تحذيرات

معدات الحماية

- يجب استخدام معدات السلامة من قبل المستخدم خلال التطبيق الذي يشمل القبعة الصلبة، قناع التنفس، نظارات السلامة، القفازات، سترة البناء، الأذذية الواقية، إلخ.

- لا تضيف الرمل أو السمنت أو أي المواد الأخرى إلى المنتج.

- لا تستخدم المنتج لإنشاء طبقات يزيد سمكها عن 6 مم.

- لا تستخدم المنتج لتطبيقات غير المذكورة في مجالات المستخدم.

- إذا كنت في شك ، فاتصل بخدمة المساعدة الفنية، الأرقام المذكورة في تحت.

- **الأسطح المسامية للغاية** ، مثل الخرسانة الخلوية، ألواح الجبس، ألواح الخشبية، إلخ.

يجب أن تستعد أولًا مع برايمير (أساس).

تستند المعلومات والتعليمات الفنية الواردة في ورقة البيانات إلى معرفة وخبرة إدارة البحث والتطوير في المصنع. نظرًا لمجموعة متنوعة من شروط التطبيق الفردية، يتم تقديم التوصيات والاقتراحات التي تشير إلى استخدام المنتج دون ضمان، نظرًا لأن ظروف الموضع

أثناء التطبيقات خارجة عن سيطرة المصنع. المستخدم وحده مسؤول عن أي تبعات ناجمة عن استخدام المنتج.



C2TE
Classification

WHITE | أبيض
GREY | رصاصي



■ TECHNICAL FEATURES ■

Form	Cementitious mortar
Consumption	3 - 5 kg/m ² depending on the trowel notch size and the nature of the substrate.
Water demand	6-7.5 liters water / 25kg & 20kg bag
Mixing Time	At least 3-5 minutes
Consistency of the mixture	Creamy thixotropic mortar
Application	Notched trowel
Maximum application thickness	6 mm
Open Time	5 - 20 minutes / Climatic conditions reduce or extend
Application Temperature	from +5°C to +40°C
Pot Life	Approx. 1 hour
Grouting on walls	after 24 hours
Grouting on floors	after 24 hours
Adhesive Strength	≥ 1 N/mm ²
Shelf Life	12 months from the date manufacturing in unopened condition. Store in a dry place and be protected from moisture.

